

Rigidur joint adhesive



Material

- Solvent-free adhesive for the bonding of joints between Rigidur and Rigidur H gypsum fibreboards.

Area of use

- For the bonding of Rigidur gypsum fibreboards in conventional drywall construction (wall, ceiling and roof structures) and in combination with Rigidur H gypsum fibreboards in wooden frame and prefabricated house construction.

Substrate properties

- All Rigidur and Rigidur H board thicknesses are in principle suitable for bonding.
- Ensure that the short edge is clean, smooth and free of dust. Cuts must be made cleanly to ensure a maximum joint width of 1 mm.

Processing

- Rigidur joint adhesive should be applied to the short edge of the first installed board direct from the cartridge using a standard gun.
- Do not allow the adhesive to come into contact with the stud framework.
- The next Rigidur gypsum fibreboard to be installed should be pressed against the joint adhesive on the first board and fastened within 10 minutes.
- Joint width: max. 1 mm.
- Excess adhesive should simply be removed with a scraper or similar once hard to create a flush surface.
- Tools can be cleaned using a thinner.
- To achieve a perfect surface finish, the bonded joint and fastening points should subsequently be filled with Rigidur joint filler.

Safety information

- The safety datasheet can be supplied to professional processors on request or found at www.rigips.de.

Technical data

Container sizes	310 ml cartridge
Material consumption	15 ml/joint m
Processing time	approx. 10 minutes
Processing temperature	5 °C to 30 °C
Storage	Can be stored for at least 12 months unopened. Use up open cartridges promptly. Not frost-sensitive.

The translation is based exclusively on the German product data sheet. Only the German product data sheet is the original, therefore errors in the translation from German into English cannot be excluded. The information in this publication is based on our current technical knowledge and experience. Due to the wide range of factors that may affect the processing and use of our products, it does not absolve users from responsibility for performing their own inspections and tests, and serves only as a general guideline. No legally binding guarantee of specific properties or suitability for a concrete purpose may be inferred. Users shall be responsible for ensuring that any trademarks and existing laws and provisions are observed at all times. We reserve the right to make changes in the interests of technical progress.