

Product data sheet

Rigidur H 18 - large format board



Product description: Homogeneous gypsum fibreboard with square edges (SK). Pre-primed, smooth and extremely hard surface. All characteristic values for load bearing calculation can be found at the European Technical Assessment ETA 08/0147. Download at www.rigips.de.

Area of application: For robust wall and ceiling systems with fire protection and sound insulation requirements and rooms. Boards in wall height are suitable for structural loads.

								
Glatte Oberfläche	Erhöhte Oberflächenhärte	Statische Zulassung	Einfache Lastenbefestigung	Anwendung Feuchtraum	Nicht brennbar A2-s1, d0	Plattendicke 18 mm	Kanten 4SK	Wetterfeste Lagerung

Technical specifications

Parameters	Sign	Value	Unit	Certification
Material				
Type of material		gypsum fibre		
Typesetting				
Type		GF-C2-I-W2		EN 15283-2
Building material class				
Fire behaviour		A2-s1, d0		EN 13501-1
Edges				
Longitudinal edge		SK		
Transverse edge		SK		
Dimensions				
Thickness	t	18.0	mm	EN 15283-2
Width	w	1250	mm	EN 15283-2
Length	l	2000 / 3000 / 3040	mm	EN 15283-2

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

Product data sheet

Rigidur H 18 - large format board

Parameters	Sign	Value	Unit	Certification
Tolerances				
Thickness		±0.9	mm	EN 15283-2
Width		+0/-2	mm	EN 15283-2
Length		+0/-2	mm	EN 15283-2
Perpendicularity: deviation per meter of width		≤ 2.0	mm/m	EN 15283-2
Nominal Weight				
Surface-related mass	≥	21.6	kg/m ²	EN 15283-2
Bulk density	≥	1200	kg/m ³	EN 15283-2
Characteristic strength values				
Bending tensile strength		5.0	N/mm ²	EN 15283-2
Surface hardness - according to Brinell		35	N/mm ²	EN ISO 6506-1
Arc resistance approved	class	LV 1.1.1.2		DIN VDE 0303-5
Heat				
Thermal conductivity	λ _{R,board}	0.35	W/(m·K)	EN ISO 10456
	λ _{10,dry}	0.202	W/(m·K)	EN 12664
Thermal expansion		0.015	mm/(m·K)	referring to EN 318
Limit load by heat (long-term exposure)		max. 50 (short-term up to 60)	°C	Gypsum data book
Humidity				
Equilibrium moisture at 20°C, 65% r.h. approx.	%	1-1.3		EN 322
Moisture expansion when the RH changes by 30% (20°C)		0.045	%	EN 318
Thickness swelling after 24h water storage	≤	2	%	referring to EN 317
Water absorption of the board surface after 30min.	≤	1500	g/m ²	EN 15283-2
Water vapour diffusion-equivalent air layer thickness	sd	0.34	m	Calculated
Water vapour diffusion resistance factor	μ	19		EN ISO 12572
Notes				
Storage		Dry Flat and level Shady Cool		
Shelf Life		Unlimited		
Form of delivery		According to Pricelist		
Waste key number		17 08 02		

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.

Product data sheet

Rigidur H 18 - large format board

The values listed in this product data sheet only reflect the performance characteristics of the products. In addition, gypsum plaster systems have structural and structural properties, which can be found in our system documentation (e. g. Planen und Bauen).

The information in this publication is based on our current technical knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve the users of our products from the responsibility of carrying out their own inspections and tests, as they only represent general guidelines. They neither do imply any legally binding assurance of certain properties or of suitability for a particular application. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and regulations are observed. We reserve the right to modifications in the interests of technical advancement without prior notice.